

# Test Report

Date: 2023/10/24

Page : 1/3

Report No.:2023605350

Customer: HandanYidao Metal Products Co.,Ltd

Address: No.183 Lianfang East Road,Handan,Hebei China

Product: Dia.36mm Thread bar grade 930

Dimension: D36 × 800 mm

Quantity: 1PC

Grade: —

Material: Grade 930

Other description: Heat No.:807880

*The information above is provided by customer who is responsible for its representativeness and authenticity.*

Sample No. : 202360535

Sample Source: Supplied by client

Sample Description: See sample photos

Receiving Date: 2023-10-18

Test Date: 2023-10-23

Specification &amp; Conformance Requirement :

The technical requirement supplied by client.

Test Result: See next page

Zhejiang Guojian Testing Technology Co.,Ltd.



电子报告



微信客服

Declaration: 1. This test report shall be invalid if without the laboratory testing seal or signatures of authorized signatory. 2. This test report shall be invalid if altered. 3. Our laboratory is only responsible for the original report. Copying, faxing, photocopying versions of the report is only for reference purpose. 4. This report is invalid if parted. 5. This test report shall not be reproduced except in full without the written approval of the laboratory. 6. This report is responsible for designated samples only. 7. Any objection of the test result should be declared timely. The tested samples will be kept for 45 days. 8. If tested samples are returned or expired, retest will no longer be offered. 9. The last digit of the report number is the version number, the original number is "0". The version number increased when this report revised, meanwhile the original report invalid, the changed information is identified in bold font. 10. If the uncertainty is not given in this report, the decision rule is simple acceptance.

No.777, Fengtan Road, Haiyan, Jiaxing, Zhejiang, China TEL:0573-86161256 86161587 Official website: <http://www.chinazhj.com>

# Test Report

Report No. : 2023605350

Page : 2/3

Test Item	Test Method	Requirement	Result	Conclusion
Tensile strength $R_m$ /MPa	GB/T 28900-2022	1080	1222	Pass
Yield strength $R_{p0.2}$ /MPa	GB/T 28900-2022	930	1102	Pass
Elongation $A/5d_0$ /%	GB/T 28900-2022	6	8.0	Pass
Elongation $A_{gt}$ /%	GB/T 28900-2022	3.5	5.5	Pass

Reviewed by : Zhang Jia Wei

Approved by : Li Bo


Test Item	Test Method	Requirement	Result	Conclusion
P/%	GB/T 4336-2016及第1号修改单	< 0.035	0.029	Pass
S/%	GB/T 4336-2016及第1号修改单	< 0.035	0.026	Pass

Reviewed by : Chen Ping

Approved by : Hu Shenhui



Sample photos




202360535-Tensile test - curve

# Test Report

Report No. : 2023605350

Page : 3/3



202360535-Tensile test-Before test



202360535-Tensile test-In test



202360535-Tensile test-After test

REPORT FINALIZED