

TEST REPORT

No. : TJIN1709012418ML Date : Sep 06, 2017 Page: 1 of 2

CUSTOMER NAME:	HANDAN YIDAO METAL PRODUCTS CO.,LTD
ADDRESS:	DEYUAN BUILDING, NO.183 LIANFANG EAST ROAD, HANDAN,
	HEBEI, China

Sample Name	:	Thread Bar Grade830/1030
Product Specification	:	Dia.32 *1000 mm
Manufacturer	:	Handan Yidao Metal Products Co.,Ltd
Material and Mark	:	PSB830
Heat No.	:	ZE21782

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

Quantity	:	1
Date of Receipt	:	Sep 04, 2017
Testing Start Date	:	Sep 04, 2017
Testing End Date	:	Sep 06, 2017
Test result(s)	:	For further details, please refer to the following page(s) (Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for SGS-CSTC Standards Technical Services(Tianjin) Co., Ltd

hou

Kevin Zhou Authorized signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-end-Conditions

Building C-11, No.80, Haiyun Street, TEDA, Tianjin, China 300457 中国・天津・经济技术开发区海云街80号C-11厂房 邮编: 300457 t (86-22) 5999 5008 f (86-22) 5999 5016 t (86-22) 5999 5008 f (86-22) 5999 5016 www.sgsgroup.com.cn e sgs.china@sgs.com



TEST REPORT

No. : TJIN1709012418ML Date : Sep 06, 2017 Page: 2 of 2

Test item: Tensile Test

Test Method: GB/T 228.1-2010

Test	Test Sample diameter		Lower Yield strength	Elongation after fracture(A)	Total elongation at maximum	Conclusion
item	(mm)	strength (MPa)	(MPa)	$L_o = 5d$	force, (Agt) %	
Req.		≥1030	≥830	≥7	≥3.5	
1	φ 32	1057	901	13.0	9.5	Pass

Note: The results comply with the requirement of GB/T 20065-2006 Type PSB830.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx.and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-en-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Clients' instructions, if any. The Company's solid client and this document does not exorerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or faisification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fulliest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. Attention:To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@gs.com

 Building C-11, No.80, Haiyun Street, TEDA, Tianjin, China 300457
 t
 (86-22) 5999 5008
 f
 (86-22) 5999 5008

www.sgsgroup.com.cn

e sgs.china@sgs.com